



Bitumen 20-30

TEST	Unit	Test Method	Grade
Pentration at 25°C	0.1mm	EN 1426	20-30
Softening Point	°C	EN 1427	55-63
Resistance to Hardening 163 °C		EN 12607-1 Or EN 12607-3	
Change of mass maximum	%		0.5
Retained penetration minimum	%		55
Softening point After Hardening minimum	°C	EN 1427	57
Flash point minimum	°C	EN 22592	240
Solubility minimum	%(m/m)	EN 12592	99.0

Please let us have your confirmation / Comment in this regard:

Email: sales@sanlierpetrol.com.tr / info@sanlipetrol.com

What`s apps: +90 530 661 9511

Tell: +90 216 341 13 97