



Bitumen 35-50

Specifications of 30-45 bitumen			
Penetration – graded Asphalt cement BS EN 12591	Test/Method	Requirement	
Softening Point °C	D36	52	60
Flash Point °C	D92	240	-
Penetration @25 °C , 01 mm	D5	35	50
Solubility in trichloroethylene , w%	D2042	99.00	-
Special weight @ 25°C,gr/cm	EN12592	To be Reported	
Rolling thin-film Oven Test	D2872	-	
Change in mass , w%	EN12607-1	0.5>	
Penetration %		53<	
Increase the softness point under normal conditions. °C or increase the softness point than usual °C		8> Or 11>	
Permeability index		NR -1.5 to +0.7	
Fraass breaking point , °C	-----	-5>OR NR	

Please let us have your confirmation / Comment in this regard:

Email: sales@sanlierpetrol.com.tr / info@sanlipetrol.com

What`s apps: +90 530 661 9511

Tell: +90 216 341 13 97