



Bitumen 50-60

Specifications of 50/60 bitumen			
Test	Unit	Requirment	
PENETRATION @25 C°	Mm/10	50-60	ASTM D5
Softening Point	C°	50-58	ASTM D36
Ductility @25 C°	CM	100	ASTM D113
Loss On heating	Wt %	1	ASTM D6
Flash point	°C	240	ASTM D92
Specific Gravity	Gr/cm3	>0.99	ASTM D70
Retained penetration (T.F.O.T)	%	52	ASTM D5
Increase in Softening Point (Max)	C°	10	ASTM D36

Please let us have your confirmation / Comment in this regard:

Email: sales@sanlierpetrol.com.tr / info@sanlipetrol.com

What`s apps: +90 530 661 9511

Tell: +90 216 341 13 97