

Bitumen 50-70

Specifications of 50/70 bitumen

Test	Unit	Requirment	
PENETRATION @25 C°	Mm/10	50-70	ASTM D5
Softening Point	C°	44-56	ASTM D36
Ductility @25 C°	CM	100	ASTM D113
Loss On heating	Wt %	0.2MAX	ASTM D6
Flash point	C°	232	ASTM D92
Specific Gravity	Gr/cm3	99.5	ASTM D70
Retained penetration (T.F.O.T)	%	68	ASTM D5
DENSITY @25 C°	Kg/m2	1.01-1.6	ASTM D70ord 3289
Spot test		NEGATIVE	A.A.S.H.O.T 102
Viscosity @135 C°	cSt	300MIN	ASTM D2170
Ductility (25 C°) 5CM/min ,after TFOT	CM	<50	ASTM D113

Please let us have your confirmation / Comment in this regard:

Email: sales@sanlierpetrol.com.tr / info@sanlipetrol.com

What`s apps: +90 530 661 9511

Tell: +90 216 341 13 97