



Bitumen 60-90

Specifications of 60-90 bitumen			
Test	Unit	Requirment	
PENETRATION @25 C°	Mm/10	60-90	ASTM D5
Softening Point	C°	40-60	ASTM D36
Ductility @25 C°	CM	100	ASTM D113
Loss On heating	Wt %	0.03	ASTM D6
Flash point	°C	230	ASTM D92
Specific Gravity	Gr/cm3	1.00-1.25	ASTM D70
Solubilite in cs2, Wt	%	60.1	ASTM D4

Please let us have your confirmation / Comment in this regard:

Email: sales@sanlierpetrol.com.tr / info@sanlipetrol.com

What`s apps: +90 530 661 9511

Tell: +90 216 341 13 97